

Flowcoat SF41



Solvent-free, pigmented, epoxy flooring system with a thickness of approx. 0.35 ÷ 3 mm.



Fast and easy application:

Epoxy resin coating applied in two layers



Chemical resistance:

Good resistance to a range of chemicals



Hard wearing:

Chemical, abrasion and sustained vehicle traffic resistant



Hygienic:

Easy-to-clean, seamless finish

Technical Information¹

REACTION TO FIRE			
B _f -s1	EN 13501-1		
SLIP RESISTANCE ²			
Dry > 40	EN 13036-4		
TEMPERATURE RESISTANCE			
Tolerant up to 70°C			
WATER PERMEABILITY			
Karsten test - Nil (Impermeable)			
SURFACE HARDNESS			
SH 285 N/mm ²	EN 13892-6		
WEAR RESISTANCE			
RWA1	EN 13892-5		
COMPRESSIVE STRENGTH			
> 80 N/mm ²	EN 13892-2		
FLEXURAL STRENGTH			
> 60 N/mm ²	EN 13892-2		
TENSILE STRENGTH			
> 15 N/mm ²	BS 6319		
IMPACT RESISTANCE			
IR10	EN ISO 6272-1		
BOND STRENGTH			
> 2,5 MPa	EN 13892-8		
SPEED OF CURE			
	10 °C	20 °C	30 °C
Light Traffic	48 hrs	16 hrs	12 hrs
Full traffic	72 hrs	48 hrs	40 hrs
Full chemical cure	12 days	7 days	7 days

Standard colour chart

Goosewing Grey Beige 326 222	Mid Grey 280	Emerald Green 740	
Yellow Grey 217	Yellow 340	Tile Red 637	Sky Blue 452

The applied colours may differ from the examples shown.
For a full colour chart and samples, contact your local Flowcrete office.

¹The figures in the table beside are typical properties achieved in laboratory tests – these results may vary depending on the conditions on the installation site.
²The final anti-slip properties of the floor are influenced by the application method, the size and shape of the aggregate used for the topcoat (aggregate recommendations available from Flowcrete Polska), the degree of abrasion, maintenance and the nature of the dirt.

Model Specification

System:	Flowcoat SF41
Finish:	Gloss
Thickness:	approx. 0,35–3,0 mm
Colour:	According to the catalog
Producer:	Flowcrete Group Ltd
Supplier:	Flowcrete Polska Sp. z o.o.
Telephone:	+48 22 879 89 07

Installation Service

The installation should be carried out by a Flowcrete approved contractors with a documented quality assurance scheme. Obtain details of our approved contractors by contacting Flowcrete Polska or enquiring via our website at www.flowcrete.com.pl.

Products Included in this System³

Primer (if weak concrete):	Peran STC or Protop 1000
First layer:	Flowcoat SF41; Natural quartz sand 0,2÷0,8 mm (optional)
Second layer:	Flowcoat SF41

³ If other resins are used contact Flowcrete Polska for further details.

Detailed application instructions are available upon request.


Substrate Requirements

Concrete or screed substrate should be class min. C20/25, a minimum bond strength of 1,5 MPa (pull-off test), surface even, clean, free from laitance, dust and other contamination. All damages in the substrate should be repaired prior to applying the flooring. The substrate should be dry up to 75% RH as per BS 8204 (5% moisture content per weight) and free from rising damp and ground water pressure. In case of higher humidity, one should use Hydraseal DPM as primer. Details to be found in the *Flowcrete Resin Flooring Substrate Requirements*.

Aftercare – Cleaning and Maintenance

Clean regularly manually or using a machine in conjunction with a mildly alkaline detergent. Flowcrete Flooring Cleaning Instruction available upon request.

System Design



Environmental Considerations

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless, impermeable surface with perfect adhesion to the substrate reduce the need for repairs and maintenance.

Technical information, recommendations and instructions concerning the product use, storage and maintenance included in this System Data Sheet are based on Flowcrete Polska Sp. z o.o. (further related as „Flowcrete“) knowledge and experience, reflecting the best acknowledged way of using the material for a given moment. Taking into consideration other factors that are beyond the producer's control, including differences in quality of substrates, tools and other complementary materials, weather conditions, proper installation and also cleaning and maintenance, Flowcrete cannot take responsibility in case of failure to conform with information and instructions included in this System Data Sheet or, respectively, written recommendations from authorized Flowcrete representatives. One should always conform with up-to-date norms and building principles, and also safety, hygiene and health protection rules according to the information included in Material Safety Data Sheets and also on the products packaging. This System Data Sheet replaces all previous versions. In order to receive up-to-date System Data Sheets contact Flowcrete Polska

[25/01/18]