

## Flowfast Kristalina

CE  
13  
PN-EN 13813

A decorative smooth sparkling fast cure MMA flooring system ideal for a modern contemporary environment.



### Rapid installation:

Developed to enable very fast track applications, therefore dramatically reducing program time



### Decorative:

Modern and contemporary look, shimmering style



### Wear Resistant:

Wear resistant surface for wheeled traffic; high chemical resistance; high scratch resistance

## Technical Information<sup>1</sup>

### SLIP RESISTANCE<sup>2</sup>

Dry > 40 EN 13036-4

### TEMPERATURE RESISTANCE

Up to 50°C

### WATER PERMEABILITY

Karsten test - Nil (Impermeable)

### WEAR RESISTANCE

AR2 EN 13892-4

### IMPACT RESISTANCE

1 kg > 1,8 m EN ISO 6272-1  
2 kg > 1,5 m


### BOND STRENGTH

Greater than cohesive strength of 25 N/mm<sup>2</sup> concrete (> 1,5 MPa)


### SPEED OF CURE

Full cure after 120 minutes

## System design




## Standard colour chart




Pacific Blue




Emerald



Cranberry



Ebony



Granite



Gold



Clementine



Peacock



Azure Blue

The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local Flowcrete office.

<sup>1</sup>The figures in the table beside are typical properties achieved in laboratory tests – these results may vary depending on the conditions on the installation site.  
<sup>2</sup>The final anti-slip properties of the floor are influenced by the application method, the size and shape of the aggregate used for the topcoat (aggregate recommendations available from Flowcrete Polska), the degree of abrasion, maintenance and the nature of the dirt.

## Model Specification

|                   |                            |
|-------------------|----------------------------|
| <b>System:</b>    | Flowfast Kristalina        |
| <b>Finish:</b>    | Satin                      |
| <b>Thickness:</b> | Approx. 2,5 mm             |
| <b>Colour</b>     | According to the catalog   |
| <b>Producer:</b>  | Flowcrete Group Ltd        |
| <b>Supplier:</b>  | Flowcrete Polska Sp. z o.o |
| <b>Telephone:</b> | +48 22 879 89 07           |

## Installation Service

The installation should be carried out by a Flowcrete approved contractors with a documented quality assurance scheme. Obtain details of our approved contractors by contacting Flowcrete Polska or enquiring via our website at [www.flowcrete.com.pl](http://www.flowcrete.com.pl).

## Products Included in this System

|                            |  |
|----------------------------|--|
| <b>Primer<sup>2</sup>:</b> | Flowfast Standard Primer   |
| <b>Bodycoat + Flakes:</b>  | Flowfast Standard Binder<br>Flowfast Pigment Powder<br>Flowfast SNL Filler<br>Kristal Flakes |
| <b>Sealer:</b>             | Flowfast Standard Seal   |

<sup>2</sup> If other resins are used contact Flowcrete Polska for further details.

Detailed application instructions are available upon request.

## Substrate Requirements

Concrete or screed substrate should be class min. C20/25, a minimum bond strength of 1,5 MPa (pull-off test), surface even, clean, free from laitance, dust and other contamination. All damages in the substrate should be repaired prior to applying the flooring. The substrate should be dry to 95% RH as per BS 8204 and free from rising damp and ground water pressure. In case of higher humidity, one should use Hydraseal DPM/Flowfast Damp Primer as primer. Details to be found in the *Flowcrete Resin Flooring Substrate Requirements*.

## Aftercare – Cleaning and Maintenance

Clean regularly manually or using a machine in conjunction with a mildly alkaline detergent. Flowcrete Flooring Cleaning Instruction available upon request.

## Environmental Considerations

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless, impermeable surface with perfect adhesion to the substrate reduce the need for repairs and maintenance.

Complies with LEED EQ Credit 4.2. requirements: VOC content < 100 g/l.

Technical information, recommendations and instructions concerning the product use, storage and maintenance included in this System Data Sheet are based on Flowcrete Polska Sp. z o.o. (further related as „Flowcrete“) knowledge and experience, reflecting the best acknowledged way of using the material for a given moment. Taking into consideration other factors that are beyond the producer's control, including differences in quality of substrates, tools and other complementary materials, weather conditions, proper installation and also cleaning and maintenance, Flowcrete cannot take responsibility in case of failure to conform with information and instructions included in this System Data Sheet or, respectively, written recommendations from authorized Flowcrete representatives. One should always conform with up-to-date norms and building principles, and also safety, hygiene and health protection rules according to the information included in Material Safety Data Sheets and also on the products packaging. This System Data Sheet replaces all previous versions. In order to receive up-to-date System Data Sheets contact Flowcrete Polska

[25/01/18]

Flowcrete Central & Eastern Europe  
ul. Marywilska 34 03-228 Warsaw Poland  
Tel: +48 22 879 8907 Fax: +48 22 879 8918  
Email: [poland@flowcrete.com](mailto:poland@flowcrete.com)

[www.flowcrete.com.pl](http://www.flowcrete.com.pl)