

Flowfast Metalika

CE
13
PN-EN 13813

A metallic fast cure MMA flooring system which contains varying sizes of metallic flakes swept over an acrylicresin base coat and finished with a clear sealer.



Rapid installation:

developed to enable very fast track applications, therefore dramatically reducing program time



Decorative:

Modern and contemporary look, shimmering style



Wear Resistant:

Wear resistant surface for wheeled traffic; high chemical resistance; high scratch resistance

Technical Information¹

SLIP RESISTANCE²

Dry > 40	EN 13036-4
----------	------------

TEMPERATURE RESISTANCE

Up to 50°C

WATER PERMEABILITY

Karsten test - Nil (Impermeable)

WEAR RESISTANCE

AR2	EN 13892-4
-----	------------

IMPACT RESISTANCE

1 kg > 1,8 m	EN ISO 6272-1
2 kg > 1,5 m	


BOND STRENGTH

Greater than cohesive strength of 25 N/mm² concrete (> 1,5 MPa)

SPEED OF CURE

Full cure after 120 minutes

System Design



Standard colour chart



Bronze



Copper



Gold



Silver

The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local Flowcrete office.

¹The figures in the table beside are typical properties achieved in laboratory tests – these results may vary depending on the conditions on the installation site.
²The final anti-slip properties of the floor are influenced by the application method, the size and shape of the aggregate used for the topcoat (aggregate recommendations available from Flowcrete Polska), the degree of abrasion, maintenance and the nature of the dirt.

Model Specification

System:	Flowfast Metalika
Finish:	Satin
Thickness:	Approx. 2,5 mm
Colour	According to the catalog
Producer:	Flowcrete Group Ltd
Supplier:	Flowcrete Polska Sp. z o.o
Telephone:	+48 22 879 89 07

Installation Service

The installation should be carried out by a Flowcrete approved contractors with a documented quality assurance scheme. Obtain details of our approved contractors by contacting Flowcrete Polska or enquiring via our website at www.flowcrete.com.pl.

Products Included in this System

Primer²:	Flowfast Standard Primer
Bodycoat + Flakes:	Flowfast Standard Binder Flowfast Pigment Powder Flowfast SNL Filler Metalika Flakes
Sealer:	Flowfast Standard Seal

² If other resins are used contact Flowcrete Polska for further details.

Detailed application instructions are available upon request.

Substrate Requirements

Concrete or screed substrate should be class min. C20/25, a minimum bond strength of 1,5 MPa (pull-off test), surface even, clean, free from laitance, dust and other contamination. All damages in the substrate should be repaired prior to applying the flooring. The substrate should be dry to 95% RH as per BS 8204 and free from rising damp and ground water pressure. In case of higher humidity, one should use Hydraseal DPM/Flowfast Damp Primer as primer. Details to be found in the *Flowcrete Resin Flooring Substrate Requirements*.

Aftercare – Cleaning and Maintenance

Clean regularly manually or using a machine in conjunction with a mildly alkaline detergent. Flowcrete Flooring Cleaning Instruction available upon request.

Environmental Considerations

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless, impermeable surface with perfect adhesion to the substrate reduce the need for repairs and maintenance.

Complies with LEED EQ Credit 4.2. requirements: VOC content < 100 g/l.

Technical information, recommendations and instructions concerning the product use, storage and maintenance included in this System Data Sheet are based on Flowcrete Polska Sp. z o.o. (further related as „Flowcrete“) knowledge and experience, reflecting the best acknowledged way of using the material for a given moment. Taking into consideration other factors that are beyond the producer's control, including differences in quality of substrates, tools and other complementary materials, weather conditions, proper installation and also cleaning and maintenance, Flowcrete cannot take responsibility in case of failure to conform with information and instructions included in this System Data Sheet or, respectively, written recommendations from authorized Flowcrete representatives. One should always conform with up-to-date norms and building principles, and also safety, hygiene and health protection rules according to the information included in Material Safety Data Sheets and also on the products packaging. This System Data Sheet replaces all previous versions. In order to receive up-to-date System Data Sheets contact Flowcrete Polska

[25/01/18]

Flowcrete Central & Eastern Europe
ul. Marywilska 34 03-228 Warsaw Poland
Tel: +48 22 879 8907 Fax: +48 22 879 8918
Email: poland@flowcrete.com

www.flowcrete.com.pl